

## Inks



## Application and Properties



## Technical Data

<b>Thickness:</b>	approx.: 360µm
<b>Basic weight:</b>	approx.: 415±10 g/m <sup>2</sup>
<b>Material:</b>	PP-PET-PP compound
<b>Surface:</b>	Smooth
<b>Adhesive type:</b>	Polyacrylate dispersion
<b>Adhesive strength:</b>	10 min: > 17,5, 24h > 17,5 (N/25mm)
<b>Liner:</b>	60µm LDPE-film

## General Information

- 360µm, 100% block out, PP-PET-PP composite
- Printable with Latex-, UV curable-, Eco Solvent- and Solvent inks
- high-tack permanent adhesive
- Suitable for cold lamination

## Application

- To enforce panel or material for indoor application
- Very suitable and developed for wall and glass panel application, e.g., kitchen splash back
- Our recommended protective film: Protect 200 Matt SoftTouch, Protect 250 glass clear

## Advantages

- White, PVC free, 100% block out
- FR certificate
- Dimension stability
- Good adhesion to the background/substrate.

## Processing instructions

- When laminating inkjet prints ensure to have sufficient drying time and the complete curing of the inks. A minimum of 24 hours is highly recommended
- Furthermore, it is recommended not to cut the material immediately after lamination, leave it for another 24 hours for a better adhesion with the printed substrate.
- Ideal conditions for application: 18 - 25°C with 40 – 65% RH

**More information**

- You can find more information on our products on [www.com2-c.de](http://www.com2-c.de)
- Always store rolls together with the label or batch number. No complaints can be processed without a batch number.
- Our tests are carried in standard climate conditions
- Shelf life in the original packaging, 1 year when storing properly at 18° - 25°C

**Available sizes**

- 30 m x 128,0 cm (50,4")

This technical information was made and assessed based on the latest technology and our experience. Due to various parameters and conditions under which the described product is used, we re-recommend that every user should check the product for its suitability for the intended uses. A legally binding assurance of certain properties cannot be derived from our information. Errors and changes are subjected. With the release of a new version, this datasheet version will not be valid.